

IP12-80S-FR(12V80Ah)

FIRE RETARDANT



Specification


Cells Per Unit	6
Voltage Per Unit	12
Nominal Capacity	80Ah@10hour-rate to 1.80V per cell @25°C
Weight	Approx. 22.0 Kg (Tolerance±3.0%)
Internal Resistance	Approx. 8.5 mΩ
Terminal	F11(M6)
Max. Discharge Current	800A (5 sec)
Short Circuit Current	1840A
Design Life	12 years (Float charging)
Max. Charging Current	24.0A
Reference Capacity	C3 61.8AH C5 70.0AH C10 80.0AH C20 84.8AH
Standby Use Voltage	13.6 V~13.8 V @ 25°C Temperature Compensation: -3mV/°C/Cell
Cycle Use Voltage	14.6 V~14.8 V @ 25°C Temperature Compensation: -4mV/°C/Cell
Operating Temperature Range	Discharge: -20°C~60°C Charge: 0°C~50°C Storage: -20°C~60°C
Normal Operating Temperature Range	25°C±5 °C
Self Discharge	Valve Regulated Lead Acid (VRLA) batteries can be stored for up to 6 months at 25°C and then recharging is recommended. Monthly Self-discharge ratio is less than 3% at 25°C. Please charge batteries before using.
Container Material	A.B.S. UL94-V0 FLAME RETARDANT



This series is a general purpose battery with 12 years design life in float service & fire retardant casing. It meets with IEC, JIS, BS, GB/T and YD/T standards. With advanced AGM valve regulated technology and high purity raw material, this series battery maintains high consistency for better performance and reliable standby service life. It is suitable for UPS/EPS, Telecom, power grid, medical equipment, emergency light and security system applications.



Dimensions



Constant Current Discharge Characteristics : A (25°C)

F.V/Time	10MIN	15MIN	30MIN	1HR	2HR	3HR	4HR	5HR	8HR	10HR	20HR
1.60V	181.9	138.2	83.3	48.9	29.1	22.6	17.7	15.1	10.1	8.44	4.41
1.65V	162.8	132.1	80.0	47.2	28.2	21.9	17.3	14.7	10.0	8.34	4.34
1.70V	149.9	123.7	76.4	45.7	27.3	21.3	16.8	14.3	9.87	8.21	4.29
1.75V	137.2	115.1	73.1	44.0	26.3	20.6	16.4	14.0	9.74	8.10	4.24
1.80V	124.2	106.3	69.8	42.3	25.4	20.0	15.9	13.6	9.57	8.00	4.20
1.85V	101.5	88.2	60.1	38.0	23.2	18.5	14.8	12.7	8.99	7.53	3.99

Constant Power Discharge Characteristics : WPC (25°C)


F.V/Time	10MIN	15MIN	30MIN	1HR	2HR	3HR	4HR	5HR	8HR	10HR	20HR
1.60V	292.8	251.6	154.4	90.9	54.6	42.7	33.7	28.8	19.6	16.4	8.61
1.65V	282.0	244.1	149.8	88.3	53.2	41.5	32.9	28.2	19.4	16.2	8.48
1.70V	264.4	232.0	144.6	86.0	51.7	40.6	32.1	27.5	19.2	16.0	8.39
1.75V	246.4	219.1	139.6	83.3	50.1	39.5	31.4	26.9	18.9	15.8	8.30
1.80V	226.9	205.1	134.8	80.6	48.6	38.5	30.6	26.3	18.7	15.6	8.22
1.85V	188.7	172.7	117.3	72.8	44.7	35.7	28.6	24.6	17.6	14.8	7.82

(Note) The above characteristics data are average values obtained within three charge/discharge cycle not the minimum values. The battery must be fully charged before the capacity test. The C₁₀ should reach 95% after the first cycle and 100% after the third cycle.


IP12-80S-FR(12V80Ah)




Discharge Characteristics Curve




Charge Characteristic Curve For Standby Use




Cycle Life In Relation To Depth Of Discharge




Relationship Between Charging Voltage And Temperature




Temperature Effects On Capacity




Storage Characteristics



Effect Of Temperature On Long Term Life



Life Characteristics Of Standby Use



(Note) All above information shall be changed without prior notice, we reserve the right to explain and update the latest information.

URL: <http://www.summitenergygroup.com.au/>